

**FICHA DE CARACTERISTICAS**

**ARENA DE SILICE GRANITO**

**ANÁLISIS GRANULOMETRICO**

<b>TAMIZ</b>	<b>PROCENTAJE (%)</b>
2-4 mm	60 -66
0.750 – 2 mm	34 – 39
0.500 – 0.750 mm	0.2 – 0.1
< 0.500 mm	0

**ANALISIS QUIMICO**

I. T. C. Fluorescencia Rayos X

SiO <sub>2</sub>	Al <sub>2</sub> O <sub>3</sub> .	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO	Na <sub>2</sub> O	K <sub>2</sub> O	TiO <sub>2</sub> .
98'6	0'53	0'03	0'08	<0'02	<0'05	0'45	0'01

Pérdida por calcinación a 1000°C. .... 0'15%